


Thermally Conductive Gap Fillers Z-Paster™ 100-20-11F Series







It applies to the liner based on silicone suitably. The flexibility and elasticity make it suited to the coating of the very uneven surfaces.

Heat can transmit to the metal housing or dissipation plate from the separate elements or even the entire PCB, which in effect enhances the efficiency and life-time of the heat-generating electronic components.

Features


- **√ROSH** » Silicone-free
- Sood thermal conductive: 2.0 W/mK
- Soft and Compressible for low stress applications
- » Available in varies thickness

Application

- > Cooling components to the chassis of frame
- Car Battery & Power Supply
- » Silicone-sensitive applications Charging Pile
- Set Top Box » Medical devices
- » LED » SFP optical module
- » Miniature heat tube radiator

Typical Properties of Z-Paster100-20-11F Series					
Color	Dark grey	Visual	Dielectric Breakdown Voltage (T= 1mm above)	>5000 VAC	ASTM D149
Construction	Silicone-free The metal oxide fills	******	Dielectric Constant	5.5 MHz	ASTM D150
Thermal Conductivity	2.0 W/mK	ASTM D5470	Volume Resistivity	6.0X10 ¹³ Ohm-meter	ASTM D257
Hardness	65 Shore 00	ASTM 2240	Continuous Use Temp	– 20 To 125 ℃	******
Specific Gravity	2.65 g/cc	ASTM D297	Outgassing (TML)	0.30%	ASTM E595
Thickness range	0.010"-0.200" (0.25mm-5.0mm)	ASTM D374	Flame Rating	94 V0	equivalent to

Product Identification:



Standard Thicknesses

0.010-inch to 0.200-inch (0.25mm to 5.0mm)

Options

Proprietary NS1 option available to eliminate tack from one side to aid in handling.

If you want to know our thermal Products, you can visit our website . http://www.ziitek.com



Gap Fillers | Pouring sealant | Silicon tape | Thermally Conductive paste | Flake graphite | Thermally Conductive Insulators | Ceramic heat sinks | Thermally Conductive plastic | Thermally Conductive Adhesive Tapes

Canada:

Tel:+001-604-2998559 E-mail: sales@thermazig.com

Taiwan:

Tel: +886-2-22771007 Fax: +886-2-22771075

E-mail: frances@ziitek.com.tw

Dongguan:

Tel: +86-769-38801208 Fax: +86-769-83791290 E-mail: angus@ziitek.com

Kunshan:

Tel: +86-512-57816297 Fax: +86-512-57816327 E-mail: kelvin@ziitek.com

Chenadu:

Tel: +86-28-62379168 Fax: +86-28-62379168 E-mail: david_cd@ziitek.com